

# CETCO® GRANULAR GROUT

## HIGH-SOLIDS GRANULAR BENTONITE GROUT



Certified to NSF/ANSI 60

### DESCRIPTION

CETCO GRANULAR GROUT mixes into a smooth bentonite grout that has no lumps and pumps easily. CETCO GRANULAR GROUT is dust-free, offers reduced friction going down the tremie pipe, and has a firm set-up with little settling. CETCO GRANULAR GROUT is certified to NSF/ANSI Standard 60, Drinking Water Treatment Chemicals - Health Effects.

### RECOMMENDED USE

CETCO GRANULAR GROUT is designed for grouting waterwells and monitoring wells, decommissioning abandoned wells and boreholes, and sealing closed-loop geothermal heat pump systems. It forms a low-permeability, flexible seal.

### CHARACTERISTICS

- Improved set-up time allows mixing flexibility and reduces settling
- Physically stable; will not flow through highly permeable soil
- Smooth consistency for improved pumping and handling

### MIXING AND APPLICATION

#### WATERWELL – 20% SOLIDS

Add one 50 lb (22.7 kg) bag of CETCO GRANULAR GROUT to 24 gallons (91 liters) of freshwater to produce 3.5 ft<sup>3</sup> (0.11 m<sup>3</sup>) of grout. Once mixed to proper consistency, grout should be pumped through a tremie pipe with a positive displacement pump from the bottom of the well up to the surface. Pumping should continue until grout at the surface reaches the initial mud weight of 9.4 lbs/gal (0.63 kg/m<sup>3</sup>).

#### GEOTHERMAL – 40% SOLIDS

Place freshwater in a paddle-mixing tank of a commercial grout mixer. Start the paddles and add one 50 lb (22.7 kg) bag of CETCO GRANULAR GROUT to the water. Mix for about 1 minute. Add silica sand at a steady rate (1-2 minutes), and continue mixing for about 2 minutes to obtain a consistent mixture. Pump with a positive displacement pump (piston pump recommended) through a 1 to 1 1/4 inch (2.54 cm to 3.18 cm) inside diameter (I.D.) tremie pipe at a rate of 5-15 gallons (19-57 liters) per minute. Yields 4.52 ft<sup>3</sup> (0.13 m<sup>3</sup>).



50 lbs (22.7 kg) CETCO GRANULAR GROUT + 100 lbs (45 kg) silica sand + 27 gallons (102 liters) freshwater 34 gallons (0.14 m<sup>3</sup>) of 40% solids grout @ 11.03 lbs/gal (0.75 kg/m<sup>3</sup>) with a Thermal Conductivity (TC) of 0.72 Btu/hr/ft/F (1.22 W/mK).

TYPICAL PROPERTIES	
Thermal Conductivity	0.43 Btu/hr/ft/F no sand 0.72 Btu/hr/ft/F, 100 lbs sand 0.73 W/mK, no sand 1.22 W/mK, 45 kg sand
Permeability	<5.2 x 10 <sup>-8</sup> cm/s
Specific Gravity	2.62 g/cm <sup>3</sup>
Max Particle Size	<300 µm

### PACKAGING

50 lb (22.7 kg) bag, 48 per pallet. All pallets are plastic-wrapped.

North America: 847.851.1800 | 800.527.9948 | www.CETCO.com

UPDATED: JULY 2015

© 2015 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit www.CETCO.com. CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

FORM: TDS\_CETCO\_GRANULAR\_GROUT\_AM\_EN\_201507

