

# CETCO<sup>®</sup> MX-80

## 30-100 MESH BENTONITE

### DESCRIPTION

CETCO MX-80 is a granular bentonite product composed of dried bentonite clay with a typical size range between 30 and 100 mesh.

### RECOMMENDED USE

May be used as a casing seal, hole abandonment material, and for sealing earthen structures.

### CHARACTERISTICS

- Less than 10% moisture
- Provides a positive seal
- Re-hydrates easily
- Will not shrink or crack

### SLURRY pH (8%)

8.0–10.0

### PACKAGING

50 lb (22.7 kg) bag, 48 per pallet. All pallets are plastic-wrapped.

### MIXING AND APPLICATION

Grouting Material	One 50 lb (22.5 kg) bag CETCO MX-80 to 24 gallons (91 liters) of water, yielding 3.5 ft <sup>3</sup> (0.1 m <sup>3</sup> ) per batch.
Dry Shallow Abandonment	Pour required amount directly down borehole; hydrate with freshwater.
Earthen Structure Seal	Normal treatment is 1-2 lbs ft <sup>3</sup> (10-20 kg/m <sup>2</sup> ), depending on soil type.

### APPEARANCE

Tan to gray granules

### BULK DENSITY

65-70 lbs/ft<sup>3</sup> (1.04–1.12 kg/m<sup>3</sup>)

### PERMEABILITY

1.0 x 10<sup>-8</sup> cm/sec

North America: 847.851.1800 | 800.527.9948 | [www.CETCO.com](http://www.CETCO.com)

UPDATED: JULY 2015

© 2015 CETCO. IMPORTANT: The information contained herein supersedes all previous printed versions, and is believed to be accurate and reliable. For the most up-to-date information, please visit [www.CETCO.com](http://www.CETCO.com). CETCO accepts no responsibility for the results obtained through application of this product. All products are sold on the understanding that the user is solely responsible for determining their suitability for the intended use and for proper use and disposal of the product. CETCO MAKES NO WARRANTY OF MERCHANTABILITY OR SUITABILITY FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH ANY SALE OF THE PRODUCTS DESCRIBED HEREIN. CETCO reserves the right to update information without notice.

FORM: TDS\_CETCO\_MX-80\_AM\_EN\_201507



**CETCO<sup>®</sup>**